# **NI-MH BATTERY DELIVERY SPECIFICATIONS**

## APPROVAL SHEET

\*\*\*\*\*\*\*\*\*\*

PRESENTED TO:

1/2 D350 L5 (6.0V 1/2D3500mAh) MODEL NO .:

4 pages including this cover page TOTAL PAGES:

**Engineering Dept** PREPARED BY:

November 12, 2015 DATE:

**CHECKED & APPROVED BY:** 













Ovonic Battery Company

#### 1. Scope

This specification governs the performance of the following Nickel-Metal Hydride cylindrical battery cell 6.0V 1/2D3500mAh.

model: 1/2D350 L5

Cell size:D.

The data involving the nominal voltage and the approximate weight of the battery pack.

#### 2. Ratings

56	70		
Unit	Specification	Conditions	
V	6.0	Unit pack	
mAh	3500	Standard charging / discharging	
mAh	3300	Standard charging / discharging	
mA	350 (0.1C)	Ta=0-45°C	
hrs	16		
mA	1750(0.5C)	-△V=40~50mv, or Timer cut-off=120% input capacity	
minute	144approx.	Temp. cut-off=45~50°C, Ta=10~40°C dT / dt=0.6°C/ min	
mA	175(0.05C)	Ta=0~45°C	
V	5.0 4.5	Less than 1.0C discharge 1.0~2.0C discharge	
mA	7000 (2.0C)	Ta= -20~50°C	
°C	-20-40	Less than 30 days	
	-20-30	Less than 90 days	
	-20-25	Less than 360 days	
%	65±20	Relative humidity	
g	380	Approx.	
	V mAh mAh mA hrs mA  minute  mA  V mA	V 6.0 mAh 3500 mAh 3300 mA 350 (0.1C) hrs 16 mA 1750(0.5C)  minute 144approx.  mA 175(0.05C)  V 5.0 4.5 mA 7000 (2.0C)  -20-40 -20-30 -20-25 % 65±20	

#### 3. Performance

Unless otherwise stated, tests should be done within one month of delivery under the following conditions:

Relative humidity: 65+20% RH

Ambient Temperature (Ta): 20+5°C

\*\*\*Notes: Standard charge / discharge condition

Charge: 350 mA (0.1C) x 16 hrs

Discharge: 700 mA (0.2C) to 5.0V/Pack

\*\*\*The batteries must be standard discharged before charging

\*\*\*Battery test vide infra:

Test	Unit	Specification	Conditions	Remarks
Capacity mA	mAh	≥3300	Standard Charge / Discharge	Up to 3 cycles
Сарасну	шдп	>3300		allowed
Open Circuit	V	≥6.25	Within 1 hr after standard	Unit cell
Voltage (OCV)	V	=0.23	charge	Unit cell
Internal	mΩ	≤80	Upon fully charge (1 Khz)	Unit cell
Impedance (Ri)	III 52	≪80		
High Rate(1.0C)		≥54	Standard charge, 1 hr rest	Dischargecut-off
Discharge	min	= 34	before discharge	voltage5.0V

Over discharge Over charge	N/A	No leakage nor explosion	350mA (0.1C) charge 1 month	
Charge Retention	mAh	≥2100(60%)	Standard charge, storage for 28 days at 20°C, standard discharge	
	mAh	≥2100(60%)	Standard charge, storage for 7 days at 40°C, standard discharge	
IEC Cycles Test	cycle	≥500	IEC 61951-2 (2003) 7.4.1.1	
Short Circuit	N/A	Deformation &leakagemay occur but no explosion	After standard charge, short circuit for 1 hr (lead wire = 2.0mm <sup>2</sup> x 20mm)	
Vibration Resistance	N/A	$\triangle$ V<0.1V $\triangle\Omega$ <25m $\Omega$ No fire No explosion	Charge at 0.1C for 16 hrs, then leave for 24 hrs. Check battery before/after vibration. Amplitude: 1.5mm, Vibration: 3000CPM any direction for 60 minutes	
Impact Resistance	N/A	$\triangle$ V<0.25V $\triangle\Omega$ <25m $\Omega$ No fire No explosion	Charge at 0.1C for 16 hrs, then leave for 30 minutes. Drop cells three times from a height of 0.5 meter onto a concrete floor. Drop along each direction of the 3 mutually perpendicular axes.	

### 4. Configurations, Dimensions And Markings

Please refer to the related drawing.

## 5. External Appearance


The cell / battery shall be free from cracks, scars, breakage, rust, discoloration, leakage and deformation

## 6. Warranty

The quality guarantee period for our products is one year.

#### 7. Cautions

- 1. Reverse charging is not acceptable.
- 2. Charge before use.
- 3. Do not charge / discharge with more than the specified current.
- 4. Do not short circuit the cell / battery.
- 5. Do not incinerate or mutilate the cell / battery.
- 6. Do not solder directly to the cell / battery.
- 7. The life expectancy may be reduced if the cell / battery is subjected to adverse conditions, like extreme temperature, deep cycling, excessive overcharge /over-discharge.
- 8. Store the cell / battery in a cool dry place.
- 9. Keep away from children. If swallowed, contact a physician at once.



Nominal Voltage: 1.2V

Nominal Capacity: 3500 mAh

Minimal Capacity: 3300 mAh

Standard Charge: 350 mA, 16hrs

Rapid Charge: 1750 mA, 2.4 (control required)

Continuous Discharge: less than 7000mA

Final Discharge Voltage: 0.9 V

Weight: 75g (Approx)

Service Life: ≥ 500 cycles

(according to IEC discharge characteristics standard)

Internal Resistance:  $12m \Omega$  (Approx)

Ambient Temperature: Standard charge: 0 ~ 45 °C

Rapid charge: 10~ 40°C

Discharge: -20 ~ 50°C

Store: (65+20% RH) Less than 30 days: -20 ~40 °C

Less than 90 days: -20 ~30 ℃

Less than360 days: -20 ~25°C


Note:

 After charge at 0.1C for 16hrs and discharge at 0.2C to 1.0V at 25 °C


2. Control required: 1) - AV: 0~5mV


2) dT / dt: 0.6°C/ min

3) Tco: 45°C~50°C



0.5C Rate Charging Curves





0.2C/0.5C/1.0C Rate Discharging Curves